

VHN561

Acrilyc Tape VHB 5611

REMARK

1. Test environment: Lab temperature 23 +/- 5°C and humidity 55 +/- 10% RH
2. Recommend operating environment temperature is 10 °C – 35 °C
3. Preserve in constant temperature and avoid being exposed to high humidity and sunligh.
4. Shelf life: 1 year under normal condition.
5. Test before using to avoid the glue being affected from the unstable substance.



VHN561

Acrilyc Tape VHB 5611

DIMENSIONS

THICKNESS	WIDTH	LENGTH
1 mm	De 6 mm a 800 mm	33 m

180° Peel Adhesive For SUS#304	>8100 (Carrier Break) g/2.5cm	>285.69 (Carrier Break) OZ/in	>79.06 (Carrier Break) N/2.5cm	PSTC-1
--------------------------------	-------------------------------	-------------------------------	--------------------------------	--------

Specification	Test Method		
Initial Tack	< 10 cm		PSTC-6 (#14ball)
Holding Power	> 72 hours	(1.0kg/2.5cm*2.5cm)	PSTC-7
Holding power for Temp. Resist 120°C	> 48 hours	(1.0kg/2.5cm*2.5cm)	PSTC-7
Dynamic Shear	> 7 kgf/cm ²	(300mm/min)	ASTM D1002